

General description

Recycled fibre based medium/fluting (CEPI code 41).

Technical Information

Properties	unit	Standard	Target Figures						
Grammage	gsm	ISO 536	100	110	120	125	135	150	175
Moisture content	%	ISO 287	8.5	8.5	8.5	8.5	8.5	8.5	8.5
CMT 30	N	ISO 7263	167	190	207	216	233	259	303
SCT CD	kN/m	ISO 9895	1.80	1.94	2.07	2.16	2.32	2.58	3.01

Properties	unit	Standard	Tolerances							
Grammage	gsm	ISO 536	±3 %							
Moisture content	%	ISO 287	+1/- 2.5 %							
CMT 30	N	ISO 7263	-10 %							
SCT CD	kN/m	ISO 9895	-10 %							

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2016

Fascination Paper