

Technical Data Sheet

AustroLiner 1

General description

Brown testliner 1 (CEPI code 10) with high strength properties and top-layer sizing.

Properties	unit	Standard	Target Figures								Tolerances
			120	135	140	150	155	160	170	200	
Grammage	gsm	ISO 536	120	135	140	150	155	160	170	200	±3 %
Moisture content	%	ISO 287	8	8	8	8	8	8	8	8	+1 / -3 %
Bursting strength	kPa	ISO 2759	379	425	442	473	489	505	537	631	-10 %
SCT CD	kN/m	ISO 9895	2.4	2.7	2.8	3.0	3.1	3.2	3.4	4.0	-10 %
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30	30	30	30	30	≤50

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from June 2026