

Technical Data Sheet

AustroSchrenz

General description

Uncoloured liner (CEPI code 53) without sizing,
for inner liner or middle liner usage.

Properties	unit	Standard	Target Figures		Tolerances
Grammage	gsm	ISO 536	90	100	±3 %
Moisture content	%	ISO 287	8	8	+1 / -3 %
Bursting strength	kPa	ISO 2759	135	150	

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from October 2020