

Technical Data Sheet

AustroLiner 2

General description

Brown testliner 2 (CEPI code 20) with top-layer sizing.

Properties	unit	Standard	Target Figures				Tolerances
Grammage	gsm	ISO 536	135	160	170	200	±3 %
Moisture content	%	ISO 287	8	8	8	8	+1 / -3 %
Bursting strength	kPa	ISO 2759	375	444	472	555	-10 %
SCT CD	kN/m	ISO 9895	2.48	2.93	3.11	3.66	-10 %
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30	≤50

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2021