

# Technical Data Sheet

## AustroLiner 1

### General description

Brown testliner 1 (CEPI code 10) with high strength properties and top-layer sizing.

| Properties         | unit | Standard | Target Figures |     |     |     | Tolerances |
|--------------------|------|----------|----------------|-----|-----|-----|------------|
| Grammage           | gsm  | ISO 536  | 120            | 135 | 160 | 200 | ±3 %       |
| Moisture content   | %    | ISO 287  | 8              | 8   | 8   | 8   | +1 / -3 %  |
| Bursting strength  | kPa  | ISO 2759 | 379            | 425 | 505 | 631 | -10 %      |
| SCT CD             | kN/m | ISO 9895 | 2.4            | 2.7 | 3.2 | 4.0 | -10 %      |
| Cobb 60 (top side) | gsm  | ISO 535  | 30             | 30  | 30  | 30  | ≤50        |

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

### Additional Information

Valid from January 2022