

Technical Data Sheet

AustroTop

General description

High performance testliner (CEPI code 55) with high strength properties, particularly suitable for cold storage and cooling chain applications.

Properties	unit	Standard	Target Figures					Tolerances
Grammage	gsm	ISO 536	120	135	150	170	186	±3 %
Moisture content	%	ISO 287	8	8	8	8	8	+1 / -3 %
Bursting strength	kPa	ISO 2759	413	463	514	549	600	-10 %
SCT CD	kN/m	ISO 9895	2.69	2.99	3.32	3.59	3.90	-10 %
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30	30	≤50
Cobb 1800 (top side)	gsm	ISO 535	100	100	100	100	100	≤125

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from January 2022