

Technical Data Sheet

AustroLiner 3

General description

Brown testliner 3 (CEPI code 30) with top-layer sizing.

Properties	unit	Standard	Target Figures										Tolerances
Grammage	gsm	ISO 536	90	100	110	115	120	135	160	170	200		±3 %
Moisture content	%	ISO 287	8	8	8	8	8	8	8	8	8		+1 / -3 %
Bursting strength	kPa	ISO 2759	200	222	244	255	267	300	355	378	444		-10 %
SCT CD	kN/m	ISO 9895	1.5	1.67	1.83	1.92	2.00	2.24	2.67	2.84	3.34		-10 %
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30	30	30	30	30	30		≤50

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2021