

General description

Brown testliner 1 (CEPI code 10) with high strength properties and top-layer sizing.

Technical Information

Properties	unit	Standard	Target Figures			
Grammage	gsm	ISO 536	120	135	160	200
Moisture content	%	ISO 287	8	8	8	8
Bursting strength	kPa	ISO 2759	379	425	505	631
SCT CD	kN/m	ISO 9895	2.4	2.7	3.2	4.0
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30

Properties	unit	Standard	Tolerances	
Grammage	gsm	ISO 536	± 3 %	
Moisture content	%	ISO 287	+1/-3 %	
Bursting strength	kPa	ISO 2759	-10 %	
SCT CD	kN/m	ISO 9895	-10 %	
Cobb 60 (top side)	gsm	ISO 535	≤ 50	

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2020