

General description

Brown testliner 2 (CEPI code 20) with top-layer sizing.

Technical Information

Properties	unit	Standard	Target Figures			
Grammage	gsm	ISO 536	135	160	170	200
Moisture content	%	ISO 287	8	8	8	8
Bursting strength	kPa	ISO 2759	375	444	472	555
SCT CD	kN/m	ISO 9895	2.48	2.93	3.11	3.66
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30

Properties	unit	Standard	Tolerances			
Grammage	gsm	ISO 536	± 3 %			
Moisture content	%	ISO 287	+1/-3 %			
Bursting strength	kPa	ISO 2759	-10 %			
SCT CD	kN/m	ISO 9895	-10 %			
Cobb 60 (top side)	gsm	ISO 535	≤ 50			

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2020