

General description

Brown testliner 3 (CEPI code 30) with top-layer sizing.

Technical Information

Properties	unit	Standard	Target Figures									
Grammage	gsm	ISO 536	90	100	110	115	120	135	160	170	200	
Moisture content	%	ISO 287	8	8	8	8	8	8	8	8	8	
Bursting strength	kPa	ISO 2759	200	222	244	255	267	300	355	378	444	
SCT CD	kN/m	ISO 9895	1.5	1.67	1.83	1.92	2.00	2.24	2.67	2.84	3.34	
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30	30	30	30	30	30	

Properties	unit	Standard	Tolerances									
Grammage	gsm	ISO 536	± 3 %									
Moisture content	%	ISO 287	+1/-3 %									
Bursting strength	kPa	ISO 2759	-10 %									
SCT CD	kN/m	ISO 9895	-10 %									
Cobb 60 (top side)	gsm	ISO 535	≤ 50									

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2020