

General description

Uncoloured liner (CEPI code 53) without sizing, for inner liner or middle liner usage.

Technical Information

Properties	unit	Standard	Target Figures	
Grammage	gsm	ISO 536	90	100
Moisture content	%	ISO 287	6	8
Bursting strength	kPa	ISO 2759	135	150

Properties	unit	Standard	Tolerances
Grammage	gsm	ISO 536	± 3 %
Moisture content	%	ISO 287	+1/-3 %

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2020

Fascination Paper