



General description

**Brown testliner 2 (CEPI code 20) with top-layer sizing.**

Technical Information

Properties	unit	Standard	Target Figures					
Grammage	gsm	ISO 536	120	135	150	160	170	200
Moisture content	%	ISO 287	8	8	8	8	8	8
Bursting strength	kPa	ISO 2759	333	375	416	444	472	555
SCT CD	kN/m	ISO 9895	2.20	2.48	2.75	2.93	3.11	3.66
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30	30	30

Properties	unit	Standard	Tolerances					
Grammage	gsm	ISO 536	±3%					
Moisture content	%	ISO 287	+1/-3%					
Bursting strength	kPa	ISO 2759	-10%					
SCT CD	kN/m	ISO 9895	-10%					
Cobb 60 (top side)	gsm	ISO 535	≤50					

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

**Valid from March 2016**