

General description

**Uncoloured liner (CEPI code 53) without sizing, for inner liner or middle liner usage.**

Technical Information

Properties	unit	Standard	Target Figures	
Grammage	gsm	ISO 536	90	100
Moisture content	%	ISO 287	6	8
Bursting strength	kPa	ISO 2759	135	150

Properties	unit	Standard	Tolerances
Grammage	gsm	ISO 536	±3%
Moisture content	%	ISO 287	+1/-3%

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

**Valid from January 2019**

Fascinating Paper