

## Technical Data Sheet

# AustroFluting R

### General description

High performance medium/fluting (CEPI code 44) with high strength properties for industrial boxes.

Properties	unit	Standard	Target Figures				Tolerances
Grammage	gsm	ISO 536	110	125	140	150	±3 %
Moisture content	%	ISO 287	8.5	8.5	8.5	8.5	+1 / -2.5 %
CMT 30	N	ISO 7263	220	250	280	300	-10 %
SCT CD	kN/m	ISO 9895	2.08	2.36	2.65	2.84	-10 %

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

### Additional Information

Valid from March 2021