

Technical Data Sheet

AustroWelle light

General description

Recycled fibre based light weight medium/fluting (CEPI code 60).

Properties	unit	Standard	Target Figures		Tolerances
Grammage	gsm	ISO 536	80	90	±3 %
Moisture content	%	ISO 287	8.5	8.5	+1 / -2.5 %
CMT 30	N	ISO 7263	95	125	indicative
SCT CD	kN/m	ISO 9895	1.41	1.65	-10 %

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from April 2026