

Technical Data Sheet

AustroWelle

General description

Recycled fibre based medium/fluting (CEPI code 41).

Properties	unit	Standard	Target Figures				Tolerances
Grammage	gsm	ISO 536	100	120	125	135	±3 %
Moisture content	%	ISO 287	8.5	8.5	8.5	8.5	+1 / -2.5 %
CMT 30	N	ISO 7263	167	207	216	233	-10 %
SCT CD	kN/m	ISO 9895	1.80	2.07	2.16	2.32	-10 %

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2021