

General description

Recycled fibre based medium/fluting (CEPI code 41).

Technical Information

Properties	unit	Standard	Target Figures			
Grammage	gsm	ISO 536	100	120	125	135
Moisture content	%	ISO 287	8.5	8.5	8.5	8.5
CMT 30	N	ISO 7263	167	207	216	233
SCT CD	kN/m	ISO 9895	1.80	2.07	2.16	2.32

Properties	unit	Standard	Tolerances
Grammage	gsm	ISO 536	± 3 %
Moisture content	%	ISO 287	+1/-2.5 %
CMT 30	N	ISO 7263	-10 %
SCT CD	kN/m	ISO 9895	-10 %

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from March 2020