

General description

Customer

Green Plasterboard Liner

General Specification

Technical Information

Properties	unit	Standard	Target Figures	
Standard				
Grammage	g/m ²	ISO 536	170	180
Grammage tolerance	g/m ²	ISO 536	± 3	± 3
Moisture QLS	%	ISO 287	10,5	10,5
Moisture QLS tolerance	%	ISO 287	± 1,5	± 1,5
Tensile strength MD	N [20 mm/min]	ISO 1924-2	200	205
Tensile strength MD min.	N [20 mm/min]	ISO 1924-2	190	195
Tensile strength CD min.	N [20 mm/min]	ISO 1924-2	58	59
Fibre orientation	MD/CD	ratio	2,9	2,9
Fibre orientation tolerance	MD/CD	ratio	± 0,4	± 0,4
Air permeability	sec/100ml	ISO 5636-5	60	60
Air permeability tolerance	sec/100ml	ISO 5636-5	+ 30	+ 30
Cobb 60 gypsum side	g/m ²	ISO 535	25	25
Cobb 60 gypsum side tolerance	g/m ²	ISO 535	-8 / +10	-8 / +10
Cobb 60 top side	g/m ²	ISO 535	20	20
Cobb 60 top side tolerance	g/m ²	ISO 535	± 5	± 5

Reel setup	unit	Target	Tolerance
Reel diameter	cm	regarding plant specifics	min. 175
Reel weight max.	to	regarding plant specifics	
Reel width	mm	regarding plant specifics	± 3
Core diameter	mm	regarding plant specifics 100 or 150	+ 5
Joints	count		max. 1 per reel, clearly marked
Winding	gypsum side	regarding plant specifics	

**Values refer to a standard atmosphere: 23°C, 50% RH.
Tensile strength refer to: 105°C, 5 Minutes**

Additional Information

Valid from January 2019

Fascination Plasterboard Liner