



General description

Customer

**Triple-ply white Plasterboard Liner,
body sized**

Technical Information

| Properties | unit | Standard | Target Figures | | | | |
|--------------------------|------------------|------------|----------------|------|------|------|------|
| Standard | | | | | | | |
| Grammage | g/m ² | ISO 536 | 160 | 170 | 18 | 190 | 200 |
| Grammage tolerance | g/m ² | ISO 536 | +/-3 | +/-3 | +/-3 | +/-3 | +/-5 |
| Moisture QLS | % | ISO 287 | 10,5 | 10,5 | 10,5 | 10,5 | 10,5 |
| Tensile strength MD | N [20mm/min] | ISO 1924-2 | 195 | 200 | 205 | 215 | 228 |
| Tensile strength MD/min. | N [20mm/min] | ISO 1924-2 | 185 | 190 | 195 | 200 | 217 |
| Fibre orientation | MD/CD | ratio | 2,9 | 2,9 | 2,9 | 2,9 | 2,9 |
| Fibre orientation/max. | MD/CD | ratio | 3,3 | 3,3 | 3,3 | 3,3 | 3,3 |
| Air permeability | sec/100ml | ISO 5636-5 | 65 | 65 | 65 | 65 | 65 |
| Air permeability/max. | sec/100ml | ISO 5636-5 | 90 | 90 | 90 | 90 | 90 |
| Cobb 60/gypsum side | g/m ² | ISO 535 | 25 | 25 | 25 | 25 | 25 |
| Cobb 60/gypsum side/min. | g/m ² | ISO 535 | 20 | 20 | 20 | 20 | 20 |
| Cobb 60/top side | g/m ² | ISO 535 | 25 | 25 | 25 | 25 | 25 |
| Cobb 60/top side/max | g/m ² | ISO 535 | 35 | 35 | 35 | 35 | 35 |

| Reel setup | unit | Tolerance |
|----------------|-------------|-----------------|
| Reel diameter | cm | max. 210cm |
| Maximum weight | to | 4to |
| Core diameter | mm | 150 or 100 |
| Reel width | mm | |
| Joints | count | max. 2 per reel |
| Winding | gypsum side | |

All values refer to a standard atmosphere: 23°C, 50% RH.

Additional Information

valid from 23.10.15

Fascination Plasterboard Liner