



General description

Customer

**Double-ply yellow Plasterboard Liner,
body sized**

Technical Information

Properties	unit	Standard	Target Figures
Standard			
Grammage	g/m ²	ISO 536	220
Grammage tolerance	g/m ²	ISO 536	+/-5
Moisture QLS	%	ISO 287	10
Tensile strength MD	N [20mm/min]	ISO 1924-2	246
Tensile strength MD/min.	N [20mm/min]	ISO 1924-2	236
Fibre orientation	MD/CD	ratio	2,9
Fibre orientation/max.	MD/CD	ratio	3,5
Air permeability	sec/100ml	ISO 5636-5	65
Air permeability/max.	sec/100ml	ISO 5636-5	90
Cobb 60/gypsum side	g/m ²	ISO 535	25
Cobb 60/gypsum side/min.	g/m ²	ISO 535	20
Cobb 60/top side	g/m ²	ISO 535	35
Cobb 60/top side/max	g/m ²	ISO 535	20

Reel setup	unit	Tolerance
Reel diameter	cm	max 220cm
Maximum weight	to	4to
Core diameter	mm	150 or 100
Reel width	mm	
Joints	count	max. 2 per reel
Winding	gypsum side	

All values refer to a standard atmosphere: 23°C, 50% RH.

Additional Information

Paper Mill Pitten PM 4
valid from 23.10.15

Fascination Plasterboard Liner