

General description

**Double coated white top liner with high ink holdout for flexo postprint.**

Technical Information

Properties	unit	Standard	Target Figures				
Grammage	gsm	ISO 536	140	150	160	180	200
Moisture content	%	ISO 287	7.5	7.5	7.5	7.5	7.5
Bursting strength	kPa	ISO 2759	290	310	330	375	400
SCT CD	kN/m	ISO 9895	2.30	2.50	2.70	2.90	3.00
Cobb 60 (top side)	gsm	ISO 535	30	30	30	30	30
Scott-Bond	J/m <sup>2</sup>	Tappi 569	280	280	280	280	280
ISO brightness	%	ISO 2470-1	80	80	80	80	80
D65 brightness	%	ISO 2470-2	84	84	84	84	84
Roughness (PPS)	µm	ISO 8791-4	1.8	1.8	1.8	2.2	2.5

Properties	unit	Standard	Tolerances	
Grammage	gsm	ISO 536	±3 %	
Moisture content	%	ISO 287	+1.5 / -2.0	
Bursting strength	kPa	ISO 2759	≤160 gsm -10 % ≤200 gsm -15 %	
SCT CD	kN/m	ISO 9895	-0.3	
Cobb 60 (top side)	gsm	ISO 535	≤50	
Scott-Bond	J/m <sup>2</sup>	Tappi 569	-40	
ISO brightness	%	ISO 2470-1	-3	
D65 brightness	%	ISO 2470-2	-3	
Roughness (PPS)	µm	ISO 8791-4	+0.7	

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

**Valid from January 2019**

Leadership in White