

General description

**White top liner (CEPI code 71) with high smoothness for printing excellence.**

Technical Information

Properties	unit	Standard	Target Figures		
Grammage*	gsm	ISO 536	125	130	160
Moisture content	%	ISO 287	7.5	7.5	7.5
Bursting strength	kPa	ISO 2759	278	285	340
SCT CD	kN/m	ISO 9895	1.80	1.85	2.30
Cobb 60 (top side)	gsm	ISO 535	35	35	35
Scott-Bond	J/m <sup>2</sup>	Tappi 569	280	280	280
ISO brightness	%	ISO 2470-1	72	72	72
D65 brightness	%	ISO 2470-2	77	77	77
Roughness (Bendtsen)	ml/min	ISO 8791-2	200	200	230

Properties	unit	Standard	Tolerances	
Grammage	gsm	ISO 536	± 3 %	
Moisture content	%	ISO 287	±1.5	
Bursting strength	kPa	ISO 2759	-10 %	
SCT CD	kN/m	ISO 9895	-10 %	
Cobb 60 (top side)	gsm	ISO 535	≤ 45	
Scott-Bond	J/m <sup>2</sup>	Tappi 569	-100	
ISO brightness	%	ISO 2470-1	- 2	
D65 brightness	%	ISO 2470-2	- 2	
Roughness (Bendtsen)	ml/min	ISO 8791-2	≤ 130gsm +100 160gsm +170	

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

**Valid from June 2019**

**\*All other grammages on request (minimum quantity 100t per order and trimmed)**

Leadership in White