

Technical Data Sheet

SpreeWhite B

General description

With top liner (CEPI code 71) with high smoothness for printing excellence.

Properties	unit	Standard	Target Figures			Tolerances
Grammage*	g/m ²	ISO 536	125	130	160	±3 %
Moisture content	%	ISO 287	7.5	7.5	7.5	±1.5 %
Bursting strength	kPa	ISO 2759	278	285	340	-10 %
SCT CD	kN/m	ISO 9895	1.80	1.85	2.30	-10 %
Cobb 60 (top side)	g/m ²	ISO 535	35	35	35	≤45
Scott-Bond	J/m ²	Tappi 569	280	280	280	-100
ISO brightness	%	ISO 2470-1	72	72	72	-2
D65 brightness	%	ISO 2470-2	77	77	77	-2
Roughness (Bendtsen)	ml/min	ISO 8791-2	200	200	230	≤ 130g/m ² +100 > 160g/m ² +170

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from October 2020

*All other grammages on request (minimum quantity 100t per order and trimmed)