

General description

White top liner (CEPI code 72) for printing excellence.

Technical Information

Properties	unit	Standard	Target Figures								
Grammage*	gsm	ISO 536	120	125	130	140	150	160	170	180	
Moisture content	%	ISO 287	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	
Bursting strength	kPa	ISO 2759	270	278	285	300	320	340	363	386	
SCT CD	kN/m	ISO 9895	1.73	1.80	1.85	1.95	2.10	2.30	2.40	2.60	
Cobb 60 (top side)	gsm	ISO 535	35	35	35	35	35	35	35	35	
Scott-Bond	J/m ²	Tappi 569	250	250	250	250	250	250	250	250	
ISO brightness	%	ISO 2470-1	67	67	67	67	67	67	67	67	
D65 brightness	%	ISO 2470-2	72	72	72	72	72	72	72	72	
Roughness (Bendtsen)	ml/min	ISO 8791-2	450	450	450	500	500	650	800	800	

Properties	unit	Standard	Tolerances	
Grammage	gsm	ISO 536	±3%	
Moisture content	%	ISO 287	±1.5	
Bursting strength	kPa	ISO 2759	-10%	
SCT CD	kN/m	ISO 9895	-10%	
Cobb 60 (top side)	gsm	ISO 535	≤45	
Scott-Bond	J/m ²	Tappi 569	-100	
ISO brightness	%	ISO 2470-1	-2	
D65 brightness	%	ISO 2470-2	-2	
Roughness (Bendtsen)	ml/min	ISO 8791-2	≤150 gsm +150 ≤180 gsm +100	

All values refer to a standard test condition ISO 187 (23°C, 50% RH)

Additional Information

Valid from June 2019

***All other grammages on request (minimum quantity 100t per order and trimmed)**

Leadership in White