

# Technical Data Sheet

## SpreeWhite C

### General description

White top liner (CEPI code 72) for printing excellence.

Properties	unit	Standard	Target Figures									Tolerances
			120	125	130	135	140	150	160	170	180	
Grammage*	g/m <sup>2</sup>	ISO 536	120	125	130	135	140	150	160	170	180	±3 %
Moisture content	%	ISO 287	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	±1.5 %
Bursting strength	kPa	ISO 2759	270	278	285	295	300	320	340	363	386	-10 %
SCT CD	kN/m	ISO 9895	1.73	1.80	1.85	1.90	1.95	2.10	2.30	2.40	2.60	-10 %
Cobb 60 (top side)	g/m <sup>2</sup>	ISO 535	35	35	35	35	35	35	35	35	35	≤45
Scott-Bond	J/m <sup>2</sup>	ISO 16260	250	250	250	250	250	250	250	250	250	-100
ISO brightness	%	ISO 2470-1	67	67	67	67	67	67	67	67	67	-2
D65 brightness	%	ISO 2470-2	72	72	72	72	72	72	72	72	72	-2
Roughness (Bendtsen)	ml/min	ISO 8791-2	450	450	450	500	500	650	800	800	800	≤ 150g/m <sup>2</sup> +150 > 150g/m <sup>2</sup> +100

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

### Additional Information

Valid from March 2021

\*All other grammages on request (minimum quantity 100t per order an trimmed)