

General description

one side smooth (egl)

Technical Information

Properties	unit	Standard	Target Figures								
Grammage	g/m ²	ISO 536	350	400	450	500	550	600	650	700	
Moisture content	%	ISO 287	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	
Thickness	µm	ISO 534	425	470	535	600	660	725	800	865	
Bending stiffness MD	mNm	Taber 7.5°	11	14	18	24	29	36	45	52	
Bending stiffness CD	mNm	Taber 7.5°	6	7	8	10	13	16	20	24	
Spec. bending stiffness MD	mNm	ISO 2493	36	46	59	79	95	118	148	171	
Spec. bending stiffness CD	mNm	ISO 2493	20	23	26	33	43	53	66	79	
ISO brightness	%	ISO 2470-1	84	84	84	84	84	84	84	84	
Cobb 60 (top side)	g/m ²	ISO 535	30	30	30	30	30	30	30	30	
Roughness Bendtsen	ml/min	ISO 8791/2	100	100	100	100	180	180	180	180	

Properties	unit	Standard	Tolerances	
Grammage	g/m ²	ISO 536	±5 %	
Moisture content	%	ISO 287	±2	
Thickness	µm	ISO 534	±5 %	
Bending stiffness MD	mNm	Taber 7.5°	±15 %	
Bending stiffness CD	mNm	Taber 7.5°	±15 %	
Spec. bending stiffness MD	mNm	ISO 2493	±15 %	
Spec. bending stiffness CD	mNm	ISO 2493	±15 %	
ISO brightness	%	ISO 2470-1	-2	
Cobb 60 (top side)	g/m ²	ISO 535	≤50	
Roughness Bendtsen	ml/min	ISO 8791/2	≤500 g/m ²	≤250
			≤700 g/m ²	≤400

All values refer to a standard test condition ISO 187 (23°C, 50% RH).

Additional Information

Valid from June 2019

Leadership in White